



- Material** NBR - Caucho Nitrilico
- Densidad** 1,25 g/cm3
- Resistencia a la Tracción** 125-130 kg/cm2
- Dureza** 80 °Sh
- Alargamiento a la Rotura** 430%
- Compresión Set 70° 24h** 7%
- Límites Térmicos** ·Temperatura Máxima Admisible: 85°C
·Temperatura Mínima Admisible: -20°C

Artículo	Ø ext	WD
EC-75/16	75	16
EC-75/23	75	23
EC-90/16	90	16
EC-90/20	90	20
EC-105/20	105	20
EC-120/18	120	18
EC-120/20	120	20
EC-120/28	120	28
EC-135/25	135	25
EC-150/20	150	20
EC-150/28	150	28
EC-175/32	175	32
EC-200/25	200	25